



**All Nydree Flooring Products with Pedestrian Finish  
Increasing the Wet Slip Resistance to 0.5 COF\*  
MatteTek™ 300 Low Gloss Finish w/ GripLok Additive  
0.55 lbs. GripLok per Gallon of MatteTek 300 Instructions**

**NOTE: Keep in mind this coating produces a grainy appearance and sandpaper-like feel.**

**SURFACE PREPARATION – Newly Installed Nydree Flooring With Pedestrian Finish**

1. Sweep and vacuum the floor to remove any loose dirt, dust or debris.
2. Abrade the Pedestrian finish using a 150 grit screen beneath a heavy, low speed (175-300 rpm), 15" to 22" diameter floor polisher. Place a red or white buffing pad between the screen and floor polisher as a driving pad. Use floor polisher with vacuum attachment to keep dust at a minimum. The surface should appear dull. Avoid dwelling on one area for a long period of time. Screen at a rate of approximately 100 square feet per minute. Just lightly abrade the Pedestrian finish. Dwelling too long could screen off the overstain found on certain Nydree flooring products. The following list of current Nydree products contain an overstain:  
COR Ice, Rift White Oak Centennial, Red Oak Harvest Wheat, Plainsawn Ash Vanilla, Maple Cider, Maple After Midnight, Maple Bella Luna, Maple Latte, Maple Tomato, Maple Sunflower, Maple Mint Green, Maple Bellaire, Hickory Mocha Rio, Cherry Essences De Rosa, Cherry Ricco Rosso, Cherry Winchester, Cherry Cherico, Plainsawn White Oak Slightly Blue.
3. Sweep, vacuum and tack rag dust.
4. Clean the floor with Bona Pro Series Hardwood Floor Cleaner. Repeat if required.
5. If any stain is removed during screening, touch up with the appropriate colored stain before continuing.

**MIXING INSTRUCTIONS – MatteTek 300 PART A & PART B (One gallon kit) with Grip-Lok Additive**

Precautions: Prior to starting this coating procedure, the temperature of the room, flooring and MatteTek 300 must be between 60 and 85 °F. Do not attempt to use MatteTek 300 when the relative humidity is greater than 80%.

1. Stir MatteTek 300 Part A and Part B thoroughly.
2. Mix the pre-measured Part A with Part B together. Hand mix thoroughly with a paint stick for two minutes, ensuring that Part A & Part B are blended together. There will be a slight color change in the mixed material. Add 25 liquid ounces of clean tap water to the mixture to aid in leveling.
3. Slowly mix in 0.55 pounds of GripLok powdered aggregate. (0.55 lbs of GripLok per gallon of mixed MatteTek 300) *This amount of GripLok per gallon must be specified when ordering from JFB Hart Coatings to achieve a wet COF of 0.5.*
4. Immediately pour the contents of the can into a clean, 10 gallon (27" x 20" x 6" or larger) all purpose, black mixing tub. This will extend the pot life (usability) of the mixture. If left in the can, the mixture will set up too quickly.

**APPLICATION INSTRUCTIONS - MatteTek 300 with GripLok Additive**

1. Apply all mixed material to the flooring within 60 minutes. Use a ¼" nap microfiber paint roller. (ArroWorthy Microfiber). Periodically stir the mixture during the 60 minutes so that the GripLok doesn't settle out.
2. Apply one coat at an application rate of 300-350 square feet per gallon. The coating is self-leveling, but avoid leaving heavy puddles and ridges.

Note: Do not re-seal the mixed product. Do not reduce the catalyzed product with water after 15 minutes. Do not mix previously catalyzed material with new material. Do not leave the mixed product in the can but immediately pour the contents into a larger container for pot life purposes.

3. Clean up with water.
4. Light traffic should not be allowed on the floor for at least 8 hours. Furniture may be replaced after twenty-four hours.
5. The new slip resistant MatteTek 300 finish can be maintained starting 5 days after applying the coating using Nydree Dust Mop Treatment and Bona Pro Series Hardwood Floor Cleaner.

One gallon kits of MatteTek 300 with 0.55 pounds of GripLok additive can be purchased at JFB Hart Coatings.

[www.jfbhartcoatings.com](http://www.jfbhartcoatings.com) Phone: 630.783.1917.

Bona Pro Series Hardwood Floor Cleaner and Dust Mop Treatment can be purchased through Nydree Flooring

Customer Service by calling 800.682.5698.

\*Tested using Brungraber Mark II Slip Tester and ASTM F-1677  
© 2015 Nydree Flooring, LLC

MatteTek™300 is a registered trademark of JFB Hart Coatings, Inc.  
02/15